## LABORATORY

OF THE

# INLAND REVENUE DEPARTMENT

BULLETIN No. 78

WHITE LEAD IN OIL

### **LABORATORY**

OF THE

# INLAND REVENUE DEPARTMENT

BULLETIN No. 78.

## WHITE LEAD IN OIL.

OTTAWA, Aug. 22, 190

W. J. GERALD, Esq., Deputy Minister of Inland Revenue.

Sir,—In accordance with the instructions of your predecessor, a collection of samples of white lead in oil, was made in the months of February and March last. 99 samples were collected in all, and submitted to the district analysts for examination. The results are shown in the subjoined table, and the following is a general view of the origin and character of the samples:—

No. of Samples.	Where Collected.	Sold as Pure But Adulterated.	Adulterated.	Genuine or Unadul- terated.
8	Halifax, N.S.	4	9	
7	St. John, N.B.	0	ī	
'R	Fredericton, N.B. Montreal, P.Q. St. Hyacinthe	1	ō	ç
5 2 3 2	Montreal, P.Q.	8	i	1
- 6	St. Hyacinthe	9	ō	9
9	St. Johns.	1	Õ	5
7	Three Rivers	0	0	6
6	Quebec	4	o l	ő
4	Ottawa, Ont. Brockville	2	2	9
7	Brockville	0	2	5
1		0	ī	9
ô		0	Õ	ĭ
122242310222	Listowel.	1	Ŏ	î
2	Palmerston	0	0	ĝ
4	Mount Forest Owen Sound	0	1	ī
2	Shelburne, Ont.	1	1	2
ā	Orangeville.	0	0	2
ĭ	Tottenham.	0	0	3
9	Allieten	0	0	ĭ
2	Alliston Collingwood	0	0	2
2	Barrie	0	0	2
2	Guelph	0	0	2
1	Berlin	1	0	ī
2	Waterloo.	U	0	1
1	Goderich	1	0	i
	Clinton	1	0	0
11	TO SHIRIFF WAR. WEAR	1	0	0
1	St. Dominace.	2	4	5
8		0	0	1
3	New Westminster	0	2	4
		0	1	2
99		25	18	56

In the foregoing statement I have distinguished between those of the adulterated samples which have been sold as 'puro' or 'genuine' and others which have been sold simply as 'white lead' or under fancy names, such as 'No. 1' 'Anchor' 'Extra' 'Compound' &c. This is in accordance with the provisions of the Act in restraint of fraudulent sale or marking, which probibits the use of the terms 'pure' or 'genuine' unless the white lead in oil has the composition defined in Schedule A of the Act in question. Out of the 99 samples collected, 56 were found to be genuine, 25 of the adulterated samples had been sold as pure, and the remaining 18 were sold without guarantee. The latter samples have all been characterised by the district analysts as 'adulterated', a perfectly justifiable proceeding on their part. This will be evident when it is considered that these sophisticated samples are in many cases marked simply 'white lead', sometimes with the words in addition, 'Warranted' 'No. 1' 'Extra' de. The amount of admixture of the 'Barytes' varies from 12 to 78 per cent. It would be equally to the advantage of the consumer and manufacturer if the percentage present of adulterant were stated on the label. Since pure dry white lead contains 86.32 per cent lead exide, it follows that, when ground with 8 per cent oil, the resulting pigment should contain

With reference to the 25 adulterated samples which were sold as pure, the vendors were required, in accordance with Section 11 of the Adulteration Act to pay the expense of collecting and analysing the samples, amounting in each case to \$9. Eighteen of these vendors complied with the demand; one appealed to the chief analyst with the result that the finding of the district analyst was confirmed; and two were relieved on showing that their samples had not been sold as pure. There still remain five vendors of this class, against whem is has been recommended that prosecutions should be instituted.

In four of the samples described in the accompanying table, the manufacturers have thought fit to print on their labels for the pure article, the words 'Government Standard'. Sites the department has not taken any action beyond carrying out the parties of the department act in restraint of Fraudulent Sale or marking it would be to discounted as the condition of discountenant the ise of the words just quoted.

I beg to come an the publication of this report and table.

A have the honour to be sir, Your obedient servant,

> THOMAS MACFARLANE, Chief Analyst.

_			Ţ				1 2	
9		4	ol o				NAME AND	Address of
Date of Cellection		No. of Sample	Onantity Purel		Sample sold as Vendo		Vendor.	Manufacturer or Furnisher as given by Ve ador.
190					8 cts.	Official Analyst, M. Bowman, Halifax, N.S.		
Feb.	19	20031	3 lbs.		0 36	Pure white lead	F. Reardon, painter	P. D. Dods & Co., Mont- real.
11	19	20032	3		0 25		W. Horton & Son,	10 10
17	19	20033	3		0 35	H & P Anchor brand decorative white lea	G. H. Cutlip, painter.	Henderson & Potts, Hali- fax, N.S.
.11	19	20034	B		0 30	Ramsay's Exterior	. Moore & Martin, paint-	A. Ramsay & Co., Mont- real.
10	20	20035	3		0.30		Black Bros. & Co.,	British North American
11	20	20036	3		0 30	London No. 1 no	ot A. J. Grant & Co.,	Paint Co., Montreal. Henderson & Potts, Hali-
11	20	20037	3 "		0 30	guaranteed pure. Green Seal brand	hardware. Crowell Bros., hard	fax, N.S. Sherwin & Williams Co., Montreal.
19	20	20038	3		0 30	pure white lead.  B B genuine white lead.	ware. Walsh Bros	Brandram Bros., London, England.
						Jenu.	St. John, N.B.	and mark
11	18	1776	3		0 30	Chemically pure	James Robertson Co. Limited.	Vendors
**	18	1776	3	Sim	0 3	"Decorators" pur lead; Association No. 357963.	e A. M. Rowan, 33	Canada Paint Co., Mont-real.
16	18	1777	0 3	(1 lb.	0 3	Pure lead	P. Nase & Son, 7	Henderson & Potts, Hali- fax, N.S.
19	19	1777	16 lt	ns.) os. (8 ns.)	0 7	2 Not guaranteed pure	Bridge street. W. H. Thorne & Co. Prince Wm. street.	British North American Colour Co.
							Fredericton, N.B.	
19	26	1777	2 3 lbs	h	0 3	"Decorators" pure.	J. G. Neill, 354 Quee street.	P. D. Dobs & Co., Mont-
11	26	1777	3 3 "		0 3	Green Seal brane strictly pure.		Sherwin & Williams Co., Montreal.
**	26	1777	43		0 3	Brandram's genuine	G. Tweeddale & Co Queen street.	Henderson & Potts, Hali- fax, N.S.
10	20	1777	53		0 3	Elephant brand; As ciation No. 59221	so-R. Chestnut & Son	Canada Paint Co., Mont- real.
						Official Analyst Dr. Fisct, Quebec.	M. Montreal.	
н	1	4 197	35 3 "		. 0	24 "Decorators" pu white lead.	r e E. Archambault, 66 Notre Dame street.	P. D. Dobs & Co., Mont-real.
11	1	4 197	86 3 "		0 :	24 Pure white lead	11	11 11
"	1	6 197	87 3 "		. 0	24 Special "decorator white lead; w ranted.	"H. Sylvester & Son, 70 St. Lawrence stree St. Hyaointhe, Que.	<b>6.</b>
	1	8 197	88 3 "		0	23 Warranted pure		el, Canada Paint Co
11			893 "				Cascade street.	de Henderson & Potts, Hali- fax, N.S.
							Montreal.	
1	. 1	9 197	91 3		. 0	27 Pure white lead	A. Beaudoin, 49	St. P. D. Dods & Co., Mont
			92 3		. 0	30 Association No. 606	Lawrence street. 1202 Wall Bros., 15b Blee	real. ry Canada Paint Co
,	,	196	92 3 11			250000000000000000000000000000000000000	street.	1

	RESULTS O	AFALTS:	н.				
Lead Oxide.	Carbon Dioxide.	Barium Sulphate.	Oil.	No. of Sample	Remarks of Official Analyst.		
p. c.	p. c.	p. c.	p.c.				
*****		61 . 13		20081	Adulterated with	tarium sulphate.	
		17:00		20082		"	
		26:58		20033		10	
		22 19		20034			
		62-51		20035			
		40.67		20036		**	
80.41				20037	Unadulterated.		
80.49				20038			
77 : 39			6.77	17768	**		
79:48			6.24	17709			
75.58			7:39	17770	86		
23.91		57:20	7.68	17771	Adulterated with	barium sulphate.	
70.34		7:59	4:79	10000	,		
80.36			4:00	17779	# ************************************	99	
79-67			4:97	17773	Unadulterated.		
77 91			7:24	17775	60 89		
74.10		6.80	7:26	19785	Adulterated with b	arium anlahata	
75.05		6.89	6:24	19986	98	"	
56.85		27:50	5.38	19787	81	"	
79.85							
79.95			7:00		Genuine.		
			5.32	15780	н		
77:25		3 · 25	7:28	19791	Adulterated with be	arium sulphata	
78-95			7:46		Genuine.	manufacte.	

	_						
1		#	arterd.			NAME AND	ADDRESS OF
Depositor		No. of Sam	Questity P.	a de	Sample sold as	Vendor.	Manufacturer or Furnisher as given by Vendor.
190	n.			8 cts.		M. Johns, Que.	
Feb.	21	19798	3 lbs	0 25	Pure white lead	J. A. Lomme, Richelieu	Dominion Oil Cloth Co.,
	21	19794	3	0 24		ntreet.	Montreal. P. D. Dode & Co., Mont-
,,	21	19795	3	0 24	Pure	mtrant.	L. Laffeur, Montreal
						Three Rivers, Que.	A. Ambent, Mcontreat
	22	10704	3	0.94	Chamically and white		
11	22				lead.	Forges street.	J. Robertson Co., Ltd., Montreal.
**	-	19797	<b>3</b> "	0 31	Seal brand; strictly pure.	Queber.	Shorwin & Williams, Montreal.
10	27	19798	8	0 30	Pure	Lapointe & Lapointe,	P. D. Dods & Co., Mont-
**	27	19799	3	0 30	10	Gauthier & Frere, St.	real. Henderson & Potts, Hali-
99	27	19800	3	0 25		Joseph street. L. C. Giguere, 214 St.	fax, N.S. P. D. Dods & Co., Mont-
61	27		3	0 25	" taken from 200	Joseph street. Pouliot & Gervais, 402	real.
					lbs barrel.	St. Joseph street.	" "
					Official Analyst, Dr. F. X. Valade, Ottawa.	Otterwes.	
н	14	20811	4 lbs	0 32	Warranted pure; from 25 lb. keg; associa- tion No. 503690.	John Storr, 404 Bank St.	Wm. Hill, Montreal
11	14	20812	3) lbs	0 25	Chemically pure; asso-	Thos. Birkett & Son,	Montreal Rolling Mills
11	14	20613	3 tins (6	0 60	Not guaranteed	Bank St.	Company.
**	14	20814	3 tins (3	0 30	H	W. Graham, Bank St.	British North America
**	14	20815	lbs.) 5 lbs. from	0 50	Guaranteed to be abso-	Geo. Philbert, 97 Clar-	P. D. Dods & Co., Mont-
**	14	20816	25 lb. keg. 25 lb. can.	1 85	intely pure.	O'Connor & O'Callag-	real.
						han Co., 819 Bank St.	
					*	Brookville, Ont.	
	15	20618	4 lbs. from 25 lb. keg.	0 32	Anchor Decorative	A. G. Dobbie & Co	Henderson & Potts, Hali-
H	15	20819	5 lbs. from 25 lb. keg.	0 40	"Decorators"; war- ranted pure; Asso- ciation No. 554231.	B. D. Steacy	fax, N.S. The Canada Paint Co., Montreal.
90	15	20820	и .,	0 40	Elephant brand; genu-		
					ine; Association No. 516306.		
11	15	20821	3 tins (9 lbs.)	0 99	Not guaranteed	R. H. Smart	Name not on label; ven- dor purchased from P.
						Kingston, Ont.	D. Dods & Co.
11	16	20622	5 lbs. from 25 lb. keg.	0 40	Elephant brand; Asso-	A. Strachan	Canada Paint Co., Mont-
11	16	20623	41 lbs. from	0 25	ciation No. 358873. Tiger brand; chemi-		real. Montreal Rolling Mills
	7.0	20824	25 lb. keg.		cally pure; Association No. 576568.		Company,
89			"		white lead.	John Corbett	
**	16		6 lbs. from 25 lb. keg.	0 48	Government Standard; pure white lead.	W. A. Mitchell	Elliott & Co., Toronto

	R	METATE OF A	HALYSON,						
Lead Oxide	Carbo	Barium fs. Sulphate	Oil.	Ne of Samp	ole.	R	emarks of Off	leial Analyst.	
p. o.	p.o.	p.e.	Pe						-
79:40			6.98	197	ms G	lenuine.			
78:40	5	8:65	6:94				-lab bt		
79 96			6.76			Adulterated with barium sulphate. Genuine.			
79.65			7.06	197	948	60			
80:35			5.95	1979					
				201	*	*			
75-45		5.40	7:34	1979		Auda A			
63 - 55		20.00	6:34	1979			ith barium so	lphate.	
72-10		7:85	8:14	1960		19	**		
74.25		6:25	7:42	1980	-	**	**		
				1000	1	**	**		
79-80	8:87		8.02	90811	Not	t adulterater	ı.		
79:44	8 79		7:94	20811	1				
35.19	4.00	50.20	8.74	20813	Ada	ilterated.			
85.87	4:22	48:36	9.99	20814					
72:30	7.82	7:47	8.20	20615					
71.30	7:50	8:17	9:24	20816	-	"			
56-57	6:29	97:84	7:38	****					
80.72	9.05		7:14	90818 90819	-	н			
				SNOTA	NOE	adulterated.			
79.63	8.44		7.98	20820		11			
19-85	5.46	34-48	8:54	90021	Adul	terated.			
0.44	8.94		7:08	30622	No.	idulterated.			
8:24	8:56		8:22	20823	-100				
						H. Clar			
1.12	5.88	89.77	7:36	20824	Adult	terated,			
8.44	8:27		8-56	20825	Not a	dulterated.			

#### RESULTS of the Examination of

ection.		ole.			bounded	CHARGON						Name and	Address of
Date of Collection.		No. of Sample			Quantity sumphased	danament l			Cost		Sample sold as	Vendor.	Manufacturer or Furnisher as given by Vendor.
190	1.							8	c	ta.	Official Analyst, Dr. W. H. Ellis, Toronto.	Stratford, Ont.	
Feb.	18	19452	3	lt.	)6.	٠.			0	24	Elephant brand; pure.	Graber & Son	Canada Paint Co., Mont- real.
,,	18	19453	3	**					0	30	Pure	Adolph & Bonnett	Elliott & Co., Toronto
"	18	19454	3	11			••		0	25	"	S. Bicker	P. D. Dods & Co., Montreal.
11	18	19455	3	**					0	25	Elephant brand ; genu	Chalmer Bros	Canada Paint Co., Mont-
11	18	19456	3	**					0	25	ine. Pure ; Association No 448413.	Wie. Lynch  Mount Forest, Ont.	real.
**	19	19457	3						0	25	Genuine : Association	J. P. Noonan	, ,
11	-	19458									No. 448185. Extra Standard	Scott & Murphy	
	-	10486								08	P	Owen Sound, Ont.	P. D. Dods & Co., Mont-
**		19459	-						-			. Chester Bros	real. Ontario Lead and Wire
31	20										Pure; Association No. 423460.	1	Co., Toronto. A. R. Ramsay & Son,
97	20	19461	3	,	•						Unicorn white lead Association No 550842.	•	Montreal.
PE	21	19462	2 3	3 ,	19				0	20	External white lead.		. " "
			-									Shelburne, Ont.	
91	21	1946	3 3	3 .	11	٠					Standard.		Elliott & Co., Toronto
99	21	1946	1 3	3	**				0	2	Pure; Champion whit lead.		Steward & Wood, Toronto
			-									Orangeville, Ont.	
99	21	1946	5 3	3	11						Standard white lead	L.I	F. Frost, Toronto
**	21	1946	6	3	17						Pure; Association No.	Adamson, Hewett Sproal.	& Canada Paint Co., Mont- real.
**	21	1946	7	3	81			1	0	2	Pure: Association No. 541970.	F. J. Marshall	Co., Toronto.
											Official Analyst, F Harrison, London, Or		
11	2	1946	8	3	**				0	2	Chemically pure	L. P. Foucar Alliston, Ont.	Jas. Robertson & Co., Toronto.
	25	2 1946	9	3	10				(	2	Pure	J. J. Cain	Elliott & Co., Toronto
11	2:		I								Pure; Elephant brand Association N c 567370.	; W. B. Clifton	R. Ramsay & Son, Mon- treal.

## 99 Samples of White Lead in Oil-Continued.

	RESULTS	OF ANALYSI	8,		
Lead Oxide.	Carbor Dioxide		Oil.	No. of Sampl	e. Remarks of Official Analyst.
р. с.	р. с.	р. с.	р. с.		
74.72	12.13		12:09	19452	Genuine.
74.60	11.23		12:58	19458	,,
65.27	8.88	13.10	11-14	19454	Adulterated by admixture with barium sulphate to the extent of 13 per cent.
81 - 40	11:55		5.23	19455	Genuine.
78:08	11.16		9.05	19456	"
76.14	9.92		11.89	19457	
35.54	4.88	28:21	30.21	19458	Adulterated by admixture with 28 per cent of
00.00					barium sulphate.
66·92 74·85	8·62 10·26	12:44	10.17	19459	Adulterated by admixture with 12 per cent of barium sulphate.
76.76	11.21		13.07	19460 19461	Genuine.
34.65	5.09	25.81	33.85	19462	Adulterated by admixture with 25 per cent of barium sulphate.
75.87	12.30		10.75	19463	Genuine.
77:04	11.65		9.87	19464	11
7.40	10.91		9.93	19465	
75.50	11.10		11.87	19466	*
5.60	10.18		12.32	19467	10
			*		•
8 32	12.20		7:60	19468	Unadulterated.
8 59	12.58		8.44	19469	
8:50	10.76		7.76	19470	11

#### RESULTS of the Examination of 99

ection.		de.	purchased.			NAME AND	Address of
Date of Collection.		No. of Sample.	Quantity pu	Cash.	Sample sold as	Vendor.	Manufacturer or Furnisher as given by Vendor.
190	1.					Collingwood, Ont.	
Feb.	22	19471	3 lba	0 25	Pure ; Association No.	White Bros	Canada Paint Co., Mon-
11	22	19472	3	0 25	557905. Pure : Association No.	J. Henderson	treal.
					594086.	Barrie, Ont.	
н	22	19473	3	0 25	Pure	Johnson & Warren	Jas. Robertson & Co.,
**	22	19474	3 ,	0 25	Pure; Association No. 567415.	J. R. Harbly Guelph, Ont.	Toronto. Canada Paint Co., Mon- treal.
11	22	19475	3	0 25	"Decorators" pure	G. A. Richardson	P. D. Dods & Co., Mon-
н	22	19476	3		Pure ; Association No.		treal. Canada Paint Co
					448461.	Berlin, Ont.	
**	22	19477	3 ,,	0 25	Pure	Peter Hyman Waterloo, Ont.	Jas. Robertson & Co., Toronto.
11	22	19479	3	0 25		M. Werchal & Son	
**	22	19480		0 25	H	Leitch & Liphardt  Goderich, Ont.	P. D. Dods & Co., Mon- treal.
**	22	19481	3 ,	0 25	"Decorators" pure		
н	22	19482	3	0 25	"	Davis & Rowlan	
					Official Analyst, E. B. Kenrick, Winnipeg, Man.	Winnipeg, Man.	
11	21	17310	3 tins	0 45	"Decorators" pure	J. H. Ashdown	Canada Paint Co., Mon-
	21	17311	3 "	0 30	Compound		treal.
10	21	17312	2 lbs	0 20	Pure; Association No.	11	
11		17313	3	0 30	Pure (Crown brand);	G. F. Stephens Co	
н	25	17314	3	0 30	Association No. 586055 Ramsay's Exterior	R. Wyatt	Ramsay & Son, Montreal
11	25	17315	3 n	0 30	"Decorators" pure	Mackensie Bros	P. D. Dods & Co., Mon-
18	26	17316	8	0 30	Pure ; Association No.	F. W. Weir & Co	treal. Canada Paint Co
**	26	17817	8	0 80	Pure; Association No. 467369.	C. A. Baskerville	w
11	26	17818	3 time (2 lbs. each)	1 00	Compound	Watt & Gordon	11
			LLL CHOLL)			St. Boniface, Man.	
19	27	17319	2 !bs	0 80	Pure ; Association No. 473026.	Allaire & Bleau	# 400000

# Samples of White Lead in Oil-Continued.

	RESULTS	OF ANALY	125.		
Lead Oxide,	Carbo Dioxid	n Bariun e. Sulphat	oil.	No. of Sampl	Demarks at On La
р. с.	р. с.	p. c.	p.c.		
79.16	13.08		7:56	1947	Unadulterated,
76.2	11.78		. 10.58	19479	
79-31	12.94		6.84 194		
79:37	12:30		7:06	19474	"
			1	194/4	11
71.96	12.08	7.96	8.00	19475	
78.98	12.86		7:34	19476	Adulterated with sulphate of barium.
			. 04	194/6	Unadulterated.
79.17	11.35		8:31	19477	
			0.01	10211	"
78-87	12:40		7:30	19479	*
65.76	9.57	17:42	6.28		"
			0 20	19480	Adulterated with barium sulphate.
49.48	7:71	31.45	9.60	*****	
		10	3 00	19481	"
69.54	10.31	7:02	10.26		
			10.00	19482	27
					•
	-				
77.71	11.42		8.69	17810	Genuine.
26.92	3.63	58.50	7:91		Adulterated.
80.50	11.49	•••••	5.63	. 1	Genuine.
78-32	11.37		8.45	17318	н
51.50	6.56	21.92	8.77	17314	Adulterated.
66-84	9.10	13.36	7.72	17315	11
77.13	10.02		7.97	17316	inc.
8.38	11:69		7.81	17317	29
3.31	3.10	60.25	10.26		dulterated.
6.53	11.80				

#### RESULT of the Examination of 99

setion.		9	rchased.			NAME AND	Address of	
Date of Colle	Date of Collection.  No. of Sample.  Quantity purchase		Quantity pur	Cash.	Sample sold as	Vendor.	Manufacturer or Furnisher as given by Vendor.	
1901						Winnipeg, Man.		
Feb.	28	17320	3 lbs	0 30	"Decorators" pure	W. R. Talbot & Co	P. D. Dods & Co	
11	28	17321	3 tins	0 65	Compound	The Jas. Robertson Co.	Vendore	
					Official Analyst, Dr. C. J. Fagan, Vic- toria, B.C.	Vancouver, B.C.		
Mar.	1	21568	15 lbs		460617		British American Paint Company	
11	1	21569	141	1 20	"Decorators " pure	McTaggart & Moserop.	P. D. Dods & Co., Mon- treal.	
99	1	21570	142 "	1 15	Pure	11 11	pp 11	
11	2	21571	12½		No. 461665		A. Ferguson & Co., Mon- treal.	
11	4	21572	14	1 20	Chemically pure; Government standard.	# *2*/-	Lead Works, Toronto.	
11	4	21573	3 2-lb.cans	0 60		H	British American Paint Company.	
91	4	21574	12½ lbs	1 10	Tiger brand; pure; Association No. 545431	Vancouver Hardware Company.	Montreal Rolling Mills.	
19	4	21575	121	1 00	Extra			
						New Westminster, B.C.		
19	5	21576	111	0 90	Pure ; Association No. 593627.	Company.	A. Kamsay & Son, Mon treal.	
н	5	21577	11	0 83	Pure ; Association No. 374277.	11 11 .	. "	
11	6	21578	3 2-lb.cans	0 60	No. 1 on cans	McTaggart & Moserop	P. D. Dods & Co., Mon	

## Samples of White Lead in Oil—Concluded.

	RESULTS O	P ANALYSIS.			Remarks of Official Analyst.	
Lead Oxide.	Carbon Dioxide,	Barium Sulphate.	Oil.	No.\ of Sample.		
p.c.	p.c.	p.e.	p.c.		-	
52:47	7.16	29.66	7.92	17320	Adulterated.	
27.13	3.78	58:24	7.99	17321	н	
86.80	8.60		8.60	21568	Genuir 9.	
72 87	10.65	15·c0	7:70	21569	Barium added; adulterated.	
75:44	5.85	11.50	7.70	21570	n	
74:69	7.10		6.50	21571	Genuine.	
87 - 87	11:40		6:80	21572	"	
5.32	4.10	78.00	9.90	21573	Adulterated with barium sulphate.	
86 67	10.80		5.70	21574	Genuine.	
7.15	7:55	45:70	C-30	21575	Adulterated with barium sulphate.	
5.20	11.90		7.10	21576	Genuine.	
6.30	11.40		7.00	21577		
7.57	2.40	70.30	9.30	21578	Adulterated with barium sulphate.	